

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 February 2003 (27.02.2003)

PCT

(10) International Publication Number
WO 03/015840 A2

- (51) International Patent Classification⁷: **A61M**
- (21) International Application Number: PCT/US02/24578
- (22) International Filing Date: 1 August 2002 (01.08.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/313,294 17 August 2001 (17.08.2001) US
10/136,246 29 April 2002 (29.04.2002) US
- (71) Applicant (*for all designated States except US*): **ADVANCED BIO PROSTHETIC SURFACES, LTD.** [US/US]; 4778 Research Drive, San Antonio, TX 78240 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **BOYLE, Christopher, T.** [US/US]; 7667 Callaghan, #601, San Antonio, TX 78229 (US). **BAILEY, Steven, R.** [US/US]; 3 Village Knoll, San Antonio, TX 78232 (US).
- (74) Agent: **ROSENBAUM, David, G.**; Rosenbaum & Associates, P.C., Suite #3600, 875 North Michigan Avenue, Chicago, IL 60611 (US).

Published:

— *without international search report and to be republished upon receipt of that report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: EMBOLIC PROTECTION DEVICE



(57) Abstract: An embolic protection device includes a catheter body having a central longitudinal lumen, a guidewire positioned within the central longitudinal lumen, and a graft member that is generally tubular in shape in an undeployed state and generally frustoconical in shape in a deployed state. A plurality of openings are formed in the graft member and a plurality of arm members interconnect a proximal end of the graft member with the catheter body. A distal end of the graft member is connected to the guidewire or the atraumatic tip. The graft member may be fabricated of superelastic materials, plastically deformable materials or self-expanding materials and the plurality of openings are capable of diametric expansion and reduction proportionate to the degree of diametric expansion and reduction of a corresponding transverse cross-sectional region of the graft member when in the deployed state to capture emboli or particulate matter and minimize extrusion of the captured material through the openings in the graft member when the graft member is collapsed.

TITLE OF THE INVENTION**[0001] EMBOLIC PROTECTION DEVICE****BACKGROUND OF THE INVENTION**

[0002] The present invention relates generally to embolic protection devices. More
5 specifically, the present invention pertains to catheter-based devices for trapping emboli, tissue, arteriosclerotic plaque or other particulate matter in the bloodstream. During angioplasty and stent implantation procedures, oftentimes emboli or other particulate matter is dislodged from the vascular wall. Once dislodged, this particulate matter enters the bloodflow and, unless trapped, collected and removed from the body in some fashion, poses a serious risk to the
10 patient.

[0003] Conventional embolic protection devices typically employ umbrella-like baskets in which structural support members are fabricated of elastically strained segments, such as stainless steel or nitinol wire or hypotubing, and rely upon the relative antegrade and retrograde movement of coaxial shafts of a catheter member to deploy and collapse the embolic basket in a
15 manner similar to the way an umbrella is opened and closed. One disadvantage of these umbrella-like devices is increased profile because the material forming the embolic basket must be folded in some manner when the basket is not deployed. Another disadvantage of umbrella-like devices is the excess flap material comprising the embolic basket when under-deployed will fold and invaginate into the lumen of the vessel causing poor apposition between the vessel
20 wall and embolic basket.

[0004] Moreover, conventional embolic protection devices are typically fashioned of materials having a relatively constant open surface area across the surface area of the embolic basket. The structure of the embolic basket in conventional embolic protection devices is such that the open spaces are dimensioned to capture emboli or other particulate matter of a certain
25 size that are dislodged as a result, for example, of the angioplasty or stent implantation procedure. With conventional embolic protection devices, the design of the device anticipates that a certain fraction of emboli or particulate matter will pass through the device and into the patient's general circulation.

BRIEF SUMMARY OF THE INVENTION

[0005] In accordance with one aspect of the invention, an embolic protection device comprising a first elongate member having a lumen, a second elongate member extending through the lumen and being movable with respect to the first elongate member, a graft member having a proximal end portion connected to the first elongate member and a distal end portion connected to the second elongate member, and a plurality of openings extending through the graft member along a length thereof is provided. The graft member is expandable from an undeployed generally tubular state to a deployed generally frustroconical state upon relative movement between the first and second elongate members in a first direction. The openings generally decrease in size from the proximal end toward the distal end when the graft member is in the deployed state to thereby capture and retain emboli and other particulate matter of different sizes.

[0006] In accordance with a further aspect of the invention, an embolic protection device comprises a catheter body having a central longitudinal lumen, a guidewire having an atraumatic tip positioned at a distal end thereof, and a graft member movable between an undeployed state and a deployed state. The guidewire is coaxially positioned within the central longitudinal lumen of the catheter body. The graft member is preferably of a generally tubular shape in the undeployed state and of a generally frustroconical shape in the deployed state. The graft member has a plurality of openings that extend along a length thereof. A plurality of arm members interconnect a proximal end of the graft member and the catheter body. A distal end of the graft member is connected to one of the guidewire and the atraumatic tip. The graft member is movable between the undeployed and deployed states upon relative movement between the catheter body and the guide wire. Preferably, the graft member is constructed of a material such that each opening expands or reduces in size in proportion to an amount of radial expansion or reduction, respectively, of a corresponding transverse cross sectional region of the graft member with which the opening is associated, to thereby capture emboli and other particulate matter when the graft member is in the deployed state and minimize extrusion of the captured material through the openings in the graft member when the graft member is in the undeployed state.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0007] The foregoing summary, as well as the following detailed description of preferred embodiments of the invention, will be better understood when read in conjunction with the appended drawings. For the purpose of illustrating the invention, there is shown in the drawings embodiments which are presently preferred. It should be understood, however, that the invention is not limited to the precise arrangements and instrumentalities shown. In the drawings:

[0008] FIG. 1 is a perspective view of a first embodiment of the inventive embolic protection device;

10 [0009] FIG. 2 is a perspective view of the first embodiment of the inventive embolic protection device in its deployed state;

[0010] FIG. 3A is a diagrammatic perspective view of a graft portion of the inventive embolic protection device in its collapsed or undeployed state;

15 [0011] FIG. 3B is a diagrammatic perspective view of the graft portion in its expanded or deployed state;

[0012] FIG. 4 is a perspective view of the first embodiment of the inventive embolic protection device in its collapsed or undeployed state with captured emboli;

[0013] FIG. 5 is a perspective view of a second embodiment of the inventive embolic protection device in its collapsed or undeployed state;

20 [0014] FIG. 6 is a perspective view of the second embodiment of the inventive embolic protection device in its expanded or deployed state;

[0015] FIG. 7 is a cross-sectional view taken along line 7-7 of FIG. 5;

[0016] FIG. 8 is a cross-sectional view taken along line 8-8 of FIG. 6;

25 [0017] FIG. 9A is a side elevational view of a third embodiment of the inventive embolic protection device in its collapsed or undeployed state; and

[0018] FIG. 9B is a side elevational view of the third embodiment of the inventive embolic protection device in its expanded or deployed state.

[0019] FIG. 10A is a side elevational view of a fourth embodiment of the inventive embolic protection device in its collapsed or undeployed state.

30 [0020] FIG. 10B is a side elevational view of the fourth embodiment of the inventive embolic protection device in its expanded or deployed state.

[0021] It is noted that the drawings are intended to represent only typical embodiments of the invention and therefore should not be construed as limiting the scope thereof. The invention will now be described in greater detail with reference to the drawings, wherein like parts throughout the drawing figures are represented by like numerals.

5

DETAILED DESCRIPTION OF THE INVENTION

[0022] Turning now to the drawings, and with particular reference to FIGS. 1-4, an embolic protection device (EPD) 10 in accordance with the present invention is illustrated. The EPD 10 is especially applicable as an in-dwelling device or for use in conjunction with an interventional device, such as a PTCA balloon catheter, for capturing emboli and/or other particulate matter within the bloodstream of a patient. The EPD 10 serves at least the dual purpose of: 1) functioning as a standard guide wire thereby allowing a catheter-borne medical device, such as a balloon dilation catheter of the type typically used for angioplasty and balloon expandable stent deployment, to be delivered to a site within a body cavity; and 2) removing particulate matter from the bloodstream that may be associated with the interventional procedure that requires use of the guide wire.

[0023] The EPD 10 preferably comprises a guidewire 12 terminated at a distal end thereof with an atraumatic tip 13, a tubular catheter body 14 coaxially and concentrically positioned about the guidewire 12 and reciprocally moveable thereupon, and a graft member or embolic basket 16 coaxially and concentrically positioned about the tubular catheter body 14 and the guidewire 12. The guidewire 12 may be tubular or solid along its entire length or may transition between solid and tubular along its length. A distal end 21 of the graft member 16 is coupled to the guidewire 12 proximal to the atraumatic tip 13 and distal to the catheter body 14. A proximal end 20 of the graft member 16 is coupled to the tubular catheter body 14 by a plurality of articulating arm members 18. The articulating arm members 18 may be constructed of braided wire.

[0024] In accordance with a preferred embodiment of the invention, the graft member 16 is fabricated of a metal, pseudometallic or polymeric film and formed either as a tubular member or as a planar member then rolled into a tubular shape. Each of the plurality of articulating arm members 18 are coupled at a first end 22 thereof to the proximal end 20 of the graft member 16 and at a second end 24 thereof to a distal region of the tubular catheter body 14.

[0025] The graft member 16 has a plurality of openings 30 that pass through a wall of the graft member 16 and communicate between an abluminal wall surface and a luminal wall surface of the graft member 16 to thereby form a porous thin-walled polymer or metallic tube. The plurality of openings 30 permit passage of body fluid, such as blood, through the graft member 16, but exclude the passage of emboli and other particulate matter when the graft member 16 is diametrically enlarged.

[0026] In accordance with a preferred embodiment of the invention, the plurality of openings 30 generally comprise a plurality of longitudinal slots formed in the graft member 16 which enlarge and open when the graft member 16 is expanded to its enlarged diameter. While it is expressly contemplated that the openings 30 may be formed as longitudinal slots in the graft member 16, those skilled in the art will appreciate that other opening geometries, such as circles, ovals, ellipses, squares, diamonds, star-shapes, polygons or the like may also be employed. Additionally, not only the geometry of the plurality of openings 30, but the sizes of the openings may be varied. By varying the size of the openings along the longitudinal axis of the graft member 16, it is possible to achieve greater control over the relative porosity of the graft member 16 along its longitudinal axis when in the expanded state in order to capture emboli and other particulate matter in the blood stream.

[0027] The particular material used to form the graft member 16 is chosen for its biocompatibility, mechanical properties, *i.e.*, tensile strength, yield strength, and, in the case where vapor deposition is employed to fabricate the graft member 16, its ease of deposition. By way of example, the graft member 16 can be constructed of a porous thin-walled polymer or metallic tube that is capable of being elastically or superelastically expanded diametrically such as to take on a generally frustoconical shape in its deployed state under the influence of a positive pressure such as that imparted by the plurality of articulating arm members.

[0028] For purposes of this application, the terms "pseudometal" and "pseudometallic" are intended to mean a biocompatible material which exhibits biological response and material characteristics substantially the same as biocompatible metals. Examples of pseudometallic materials include, for example, composite materials and ceramics. Composite materials are composed of a matrix material reinforced with any of a variety of fibers made from ceramics, metals, or polymers. The reinforcing fibers are the primary load carriers of the material, with the matrix component transferring the load from fiber to fiber. Reinforcement of the matrix

material may be achieved in a variety of ways. Fibers may be either continuous or discontinuous. Reinforcement may also be in the form of particles. Examples of composite materials include those made of carbon fibers, boron fibers, boron carbide fibers, carbon and graphite fibers, silicon carbide fibers, steel fibers, tungsten fibers, graphite/copper fibers, titanium and silicon carbide/titanium fibers.

[0029] The graft member 16 may be fabricated of pre-existing convention wrought materials, such as stainless steel or nitinol hypotubes, or may be fabricated by thin film techniques. In addition to wrought materials that are made of a single metal or metal alloy, the inventive grafts may comprise a monolayer of biocompatible material or of a plurality of layers of

biocompatible materials. Laminate structures are generally known to increase the mechanical strength of sheet materials, such as wood or paper products. Laminates are used in the field of thin film fabrication also to increase the mechanical properties of the thin film, specifically hardness and toughness. Laminate metal foils have not been used or developed because the standard metal forming technologies, such as rolling and extrusion, for example, do not readily lend themselves to producing laminate structures. Vacuum deposition technologies can be developed to yield laminate metal structures with improved mechanical properties. In addition, laminate structures can be designed to provide special qualities by including layers that have special properties such as superelasticity, shape memory, radio-opacity, corrosion resistance etc.

[0030] The metals contemplated include, without limitation, the following: titanium, vanadium, aluminum, nickel, tantalum, zirconium, chromium, silver, gold, silicon, magnesium, niobium, scandium, platinum, cobalt, palladium, manganese, molybdenum and alloys thereof, such as zirconium-titanium-tantalum alloys, nitinol, and stainless steel. Additionally, in the case where multiple layers and/or laminates of films are employed, each layer of material used to form the graft may be doped with another material for improving properties of the material, such as radio-opacity or radioactivity, for example by doping with tantalum, gold, or radioactive isotopes.

[0031] When the EPD 10 is in its undeployed or collapsed state, as depicted in FIG. 1, each of the plurality of articulating arm members 18 is positioned parallel to a longitudinal axis of the EPD 10. When relative movement between the guidewire 12 and the catheter body member 14 occurs, such as by antegrade movement of the guidewire 12 or retrograde movement of the

catheter body member 14, each of the articulating arm members 18 are urged from their longitudinal orientation into a generally radial orientation relative to the longitudinal axis of the EPD 10.

[0032] As each of the articulating arm members 18 undergo their orientational change, a positive pressure is exerted by the plurality of articulating arm members 18 to the proximal end 20 of the graft member 16, which then undergoes a geometric change and diametrically enlarges from its undeployed diameter D_1 to its enlarged deployed diameter D_2 , as depicted in FIGS. 3A and 3B. The diametric change of the graft member 16 from D_1 to D_2 is preferably an elastic or superelastic deformation in which D_1 is associated with the low strain configuration of the graft member 16. However, in the case where D_2 is associated with the low strain configuration, release of a constraining force exerted by arms 18 can permit self-expansion of the graft member 16. The diametric change of the graft member 16 from D_1 to D_2 may also be associated with a plastic deformation.

[0033] In one embodiment, the articulating arm members may have a low strain configuration that is associated with the collapsed diameter D_1 . In this embodiment, a compressive load is applied to the articulating arm members 18 when either the guidewire 12 or the catheter body member 14 are moved relative to one another thus causing the articulating arm members to buckle outward and enlarging the proximal end 20 of the graft member 16 to D_2 . The articulating arm members 18 and the graft member 16 assume their collapsed configurations upon removal of the compressive load.

[0034] In a further embodiment, the articulating arm members 18 may alternatively have a low strain configuration that is associated with the deployed diameter D_2 . In this embodiment, a tensile load must be maintained in the articulating arm members 18 to keep the articulating arm members 18 and the graft member 16 in the collapsed state D_1 . The articulating arm members 18 and the graft member 16 assume their respective deployed configurations upon removal of the tensile load when either the guidewire 12 or the catheter body member 14 are moved relative to one another. The articulating arm members 18 and the graft member 16 reassume their respective collapsed configuration upon reapplication of the tensile load.

[0035] In accordance with a preferred embodiment of the present invention, the graft member 16 is fabricated of a superelastic material which is capable of undergoing two-way transition between an austenite phase to a martensite phase as a result of stress and strain applied through

the plurality of articulating arm members 18 to diametrically expand and diametrically collapse the graft member 16.

[0036] Preferably, the distal end 21 of the graft member 16 does not undergo any or any appreciable diametric expansion. However, during diametric expansion of the proximal end 20 of the graft member 16, the graft member 16 assumes a generally frustoconical shape with a taper of the graft member from its proximal end 20 to its distal end 21.

[0037] Because the graft member 16 undergoes differential diametric expansion along its longitudinal axis, the relative degree of expansion of the plurality of openings 30 along the longitudinal axis of the graft member 16 will also vary. The openings 30 toward the proximal end 20 of the graft member 16 will exhibit a greater degree of expansion than will the openings 30 toward the distal end 21 of the graft member 16. Thus, in its expanded state, the graft member 16 will have a differential open surface area along its longitudinal axis. With this arrangement, the larger diametric region of the graft member 16 has larger openings in closer proximity to the walls of the blood vessel and the relatively slower region of the fluid flow through the blood vessel, where larger, slower moving emboli and particulate matter is more likely to be located in the blood flow. Conversely, the distal region of the graft member 16 has smaller openings in closer positional proximity to a central luminal region of the blood flow, where there is a relatively faster rate of fluid flow and where the smaller, faster moving, emboli and particulate matter is more likely to be found in the blood flow. The EPD 10, therefore, exposes the blood flow distal an interventional device to a gradient of openings in the graft member 16 which more closely approximates the blood flow velocities relative to the transverse cross-sectional area of the vasculature and positions dimensionally sized openings in a more correct orientation relative to the blood flow velocities than with conventional devices. The expansive feature of the EPD 10 also allows for improved apposition of the graft member 16 to the vessel wall regardless of the expansion ratio D_2/D_1 , particularly since the graft member 16 is not subject to folding, as in the prior art.

[0038] Additionally, relative movement of either the guidewire 12 or the catheter body member 14, depending on the embodiment of the present invention, collapses the graft member 16 with a concomitant reduction in size of the openings 30. As depicted in FIG. 4, any emboli or particulate matter 5 is captured and sequestered within the lumen of the graft member 16. During contraction of the graft member 16, the size of the openings 30 also reduces, which

minimizes undesired extrusion of the captured emboli and particulate matter through the openings 30 and ejection of the extrudate into the blood flow of the patient. Thus, a greater quantum of emboli and other particulate matter is both captured and withdrawn from the body with the present invention than is found with conventional embolic protection devices.

5 [0039] FIGS. 5-8 illustrate an embolic protection device 50 in accordance with a further embodiment of the invention. Like the EPD 10, the EPD 50 also generally comprises a graft member 52 fabricated of metal, polymeric or pseudometallic materials as described above, a guidewire 54, and a catheter body member 58. The graft member 52 is preferably fabricated of a mesh material having a woven web 51 and a plurality of interstitial spaces 55 within the
10 woven web 51. The graft member 52 is coaxially and concentrically positioned about the guidewire 54. The catheter body member 58 is also coaxially and concentrically positioned about the guidewire 54. The catheter body member 58 is interconnected with a proximal end 53 of the graft member 52 by a plurality of arms 60. Each of the plurality of arms 60 is preferably oriented parallel to the longitudinal axis of the EPD 50 when the EPD is in its
15 undeployed state. When the EPD 50 is in its undeployed state, a distal end of the catheter body member may be proximally positioned relative to the proximal end of the graft member 52, or it may be concentrically positioned between the graft member 52 and the guidewire 54. A distal end of the graft member 54 is coupled either to the guidewire 54 or to an atraumatic tip 56.

[0040] Relative movement of either the guidewire 54 and atraumatic tip 56 in a retrograde
20 direction or of the catheter body 58 in an antegrade direction, exerts an applied pressure to the plurality of arms 60 causing flexion of the plurality of arms 60 from the longitudinal axis and into a radial orientation, and the arms exert a radially expansive force to the proximal end 53 of the graft member 52.

[0041] In another embodiment, relative movement of either the guidewire 54 and atraumatic
25 tip 56 in a retrograde direction or of the catheter body 58 in an antegrade direction reduces or removes a tensile stress present in the articulating arm members 60 such as to allow the articulating arm members 60 to assume a lower strain deployed configuration.

[0042] As depicted in FIGS. 6 and 8, the proximal end 53 of graft member 52 diametrically enlarges and urges the graft member 52 from a tubular shape to a frustroconical shape. Again,
30 like EPD 10, the interstitial openings 55 in EPD 50 also enlarge proportionate to the degree of diametric enlargement of the corresponding transverse cross-sectional area of the graft 52.

Again, when the EPD 50 is in its deployed state, there is a differential open surface area along the longitudinal axis of the graft member 52 that presents a gradient in open surface area. Similar to EPD 10, when the graft member 52 is collapsed, the enlarged interstitial openings 55 in web 51 reduce in size to capture emboli and particulate matter within the graft member 52 while minimizing extrudate through the openings 55 during collapse.

[0043] Like the EPD 10, the graft member 52 is preferably fabricated of a superelastic material and is capable of undergoing two-way transformation from the austenite to the martensite phase under the influence of an applied stress and strain from relative movement of the guidewire 54 and catheter body 58 through the plurality of arms 60. Each of the plurality of arms 60 may also be fabricated of superelastic material and have both an austenitic phase shape and a martensitic phase shape corresponding to the transformation shapes of the graft member 52. By fabricating both the graft 52 and the plurality of arms 60 of superelastic materials, the relative movement of the guidewire 54 and the catheter body member 58 exerts an applied stress-strain to the arms 60 and graft member 52 sufficient to cause phase transition and, therefore, geometries of the arms 60 and graft member 52. Alternatively, the graft member 52 and the plurality of arms 60 may be fabricated of like plastically deformable or self-expanding materials, such as stainless steel, or may be fabricated of different materials, with the arms 60 being fabricated of a self-expanding elastically, plastically or superelastically deformable material and the graft member 54 being fabricated of an elastic or superelastic material. Thus, the arms 60 and the graft member 54 may be fabricated of like or different materials that exhibit like or distinct material properties.

[0044] FIGS. 9A and 9B illustrate an embolic protection device 70 in accordance with other embodiments of the invention. The EPD 70 is similar in construction to the EPD 10, with the exception that the articulating arm members 18 are replaced by articulating arm members 72 that are integrally formed in a distal portion of the catheter body member 14. The articulating arm members 72 are formed by cutting slits 74 into a distal tubular portion of the catheter body member 14. As shown, the slits extend longitudinally along the catheter body member 14. Alternatively, the slits may spiral around a portion of the catheter body member 14. The graft member 16 is placed concentrically around a distal portion of the catheter body member 14, such that it is over the arm members 72 and slits 74. The catheter body member 14 and the graft member 16 are connected (e.g., by welding) to the guide wire 12 at the distal end of the

catheter body member 14 and graft member 16 by connection 76. In the embodiment shown in FIG. 9A, the articulating arm members 72 are shape set in a closed configuration. To deploy the graft member 16, the catheter body member 14 is moved distally while the guide wire 12 is not moved, thereby causing articulating arm members 72 to buckle outward and deploy the graft member 16. In the embodiment shown in FIG. 9B, the articulating arm members 72 may also have a low strain configuration that is associated with the deployed diameter D_2 of the graft member 16. The catheter body member 14 is pulled proximally with respect to the guide wire 12 to maintain tension with the guide wire 12 such that the articulating arm members 72 are straightened and the graft member 16 remains in an undeployed ("captured") state.

Relieving the tension between the guide wire 12 and the catheter body member 14 by moving the catheter body member 14 distally with respect to the guide wire 12, the arm members 72 return to an open shape such that graft member 16 is deployed.

[0045] FIGS. 10A and 10B illustrate an embolic protection device 80 in accordance with another embodiment of the invention. The EPD 80 is similar in construction to the EPD 10, with the exception that the articulating arm members 18 are replaced by articulating arm members 82 that are integrally formed in a distal portion of the guidewire 12. The articulating arm members 82 are formed by cutting slits 84 into a distal tubular portion of the guidewire 12, when at least a portion of the guide wire 12 is of tubular shape. As shown, the slits extend longitudinally along the guide wire 12. Alternatively, the slits may spiral around a portion of the guide wire 12. The graft member 16 is placed concentrically around a distal portion of the guide wire 12, such that it is over the arm members 82 and slits 84 and can be connected (e.g., by welding) to the guide wire 12 at the distal end of the graft member by connection 86. In this embodiment, the articulating arm members 82 may also have a low strain configuration that is associated with the deployed diameter D_2 and the catheter body member 14 acts as a capture sheath such that in the captured state, the catheter body member 14 prevents the articulating arm members 82 from expanding the graft member 16. With this arrangement, the catheter body member 14 is retracted for deployment of the articulating arm members 82 which in turn force the graft member into the deployed or expanded condition, as shown in FIG. 10B. Likewise, the catheter body 14 can be moved in the opposite direction to force the articulating arm members 82, and thus the graft member 16, to their collapsed or undeployed condition as

shown in FIG. 10A. It will be understood that the articulating arm members can alternatively be in the form of wire like attachments connected to the distal end of the guidewire 12.

[0046] Thus, it will be appreciated by those of ordinary skill in the art that the inventive embolic protection device is suitable for use alone as an in-dwelling device or for use in
5 conjunction with a balloon catheter, for capturing emboli and/or other particulate matter within the bloodstream of a patient. Moreover, the embodiments of the inventive embolic protection device employ a porous graft that is urged, either under the influence of superelastic phase transformation, plastic deformation or self-expanding properties, into a frustroconical shape having a proximal end that is diametrically enlarged to capture emboli and other particulate
10 matter, then is collapsible to capture the matter within the graft with a minimal degree of extrusion of particulate matter through the pores of the graft. The porous openings in the graft are differentially expansible proportionate to the degree of expansion of a corresponding transverse cross-sectional region of the graft member, where the porous openings differentially expand and contract during deployment and collapse of the graft to capture the particulate
15 matter therein.

[0047] When the inventive embolic protection device is withdrawn from the body, the emboli and particulate matter within the graft member are captured and sequestered. In conventional devices that are characterized by more static open regions, there is a tendency for the emboli and particulate matter to extrude through the open regions when the embolic device is
20 collapsed. Because conventional devices employ more constant area of open region, a greater quantum of emboli and particulate matter will be ejected by extrusion through the open regions. However, with the present invention, the dimension of the open regions changes during diametric expansion and during diametric contraction. Because there is a reduction in the dimension of the open regions during diametric contraction, the present invention is
25 substantially less susceptible to embolic extrusion through the graft member during collapse of the graft member. Thus, a greater quantum of emboli and other particulate matter is both captured and withdrawn from the body with the present invention than is found with conventional embolic protection devices.

[0048] EXAMPLE 1

30 [0049] In accordance with the preferred embodiment of fabricating the inventive microporous metallic implantable device in which the device is fabricated from vacuum deposited nitinol

tube, a cylindrical deoxygenated copper substrate is provided. The substrate is mechanically and/or electropolished to provide a substantially uniform surface topography for accommodating metal deposition thereupon. A cylindrical hollow cathode magnetron sputtering deposition device was employed, in which the cathode was on the outside and the substrate was positioned along the longitudinal axis of the cathode. A cylindrical target consisting either of a nickel-titanium alloy having an atomic ratio of nickel to titanium of about 50-50% and which can be adjusted by spot welding nickel or titanium wires to the target, or a nickel cylinder having a plurality of titanium strips spot welded to the inner surface of the nickel cylinder, or a titanium cylinder having a plurality of nickel strips spot welded to the inner surface of the titanium cylinder is provided. It is known in the sputter deposition arts to cool a target within the deposition chamber by maintaining a thermal contact between the target and a cooling jacket within the cathode. In accordance with the present invention, it has been found useful to reduce the thermal cooling by thermally insulating the target from the cooling jacket within the cathode while still providing electrical contact to it. By insulating the target from the cooling jacket, the target is allowed to become hot within the reaction chamber. Two methods of thermally isolating the cylindrical target from the cooling jacket of the cathode were employed. First, a plurality of wires having a diameter of 0.0381mm were spot welded around the outer circumference of the target to provide an equivalent spacing between the target and the cathode cooling jacket. Second, a tubular ceramic insulating sleeve was interposed between the outer circumference of the target and the cathode cooling jacket. Further, because the Ni-Ti sputtering yields can be dependant on target temperature, methods which allow the target to become uniformly hot are preferred.

[0050] The deposition chamber was evacuated to a pressure less than or about 2.5×10^{-7} Torr and pre-cleaning of the substrate is conducted under vacuum. During the deposition, substrate temperature is preferably maintained within the range of 300 and 700 degrees Centigrade. It is preferable to apply a negative bias voltage between 0 and -1000 volts to the substrate, and preferably between -50 and -150 volts, which is sufficient to cause energetic species arriving at the surface of the substrate. During deposition, the gas pressure is maintained between 0.1 and 40 mTorr but preferably between 1 and 20 mTorr. Sputtering preferably occurs in the presence of an Argon atmosphere. The argon gas must be of high purity and special pumps may be employed to reduce oxygen partial pressure. Deposition times will vary depending upon the

desired thickness of the deposited tubular film. After deposition, the plurality of microperforations are formed in the tube by removing regions of the deposited film by etching, such as chemical etching, ablation, such as by excimer laser or by electric discharge machining (EDM), or the like. After the plurality of microperforations are formed, the formed

5 microporous film is removed from the copper substrate by exposing the substrate and film to a nitric acid bath for a period of time sufficient to remove or dissolve the copper substrate.

[0051] While the invention has been taught with specific reference to the above-described embodiments, those skilled in the art will recognize that changes can be made in form and detail without departing from the spirit and the scope of the invention. Thus, the described
10 embodiments are to be considered in all respects only as illustrative and not restrictive. The scope of the invention is, therefore, indicated by the appended claims rather than by the foregoing description. All changes that come within the meaning and range of equivalency of the claims are to be embraced within their scope.

6. An embolic protection device according to claim 5, wherein relative movement of the first and second elongate members in a second direction opposite the first direction causes the graft member to return to the undeployed state, thereby reducing the size of the openings at least at the proximal end, such that the emboli and other particulate matter can be entrapped within the graft member.

7. An embolic protection device according to claim 6, wherein the openings are substantially uniform in size when the graft member is in the undeployed state.

8. An embolic protection device according to claim 7, wherein the graft member is constructed from at least one of a superelastic material, a plastically deformable material, and an elastic material.

9. An embolic protection device according to claim 1, wherein the graft member is constructed from at least one of a superelastic material, a plastically deformable material, and an elastic material.

10. An embolic protection device according to claim 1, wherein the distal end of the graft member is substantially restrained against radial expansion such that the graft member decreases in diameter from the proximal end toward the distal end when the graft member is in the deployed state.

11. An embolic protection device according to claim 10, wherein the size of each opening is proportional to the diameter of the graft member at which each opening is located.

12. An embolic protection device according to claim 1, wherein relative movement of the first and second elongate members in a second direction opposite the first direction causes the graft member to return to the undeployed state, thereby reducing the size of the openings at least at the proximal end, such that the emboli and other particulate matter can be entrapped within the graft member.

13. An embolic protection device according to claim 1, wherein the graft member is constructed of a metal material.

14. An embolic protection device according to claim 1, wherein the graft member is constructed of a thin film metal.

15. An embolic protection device according to claim 14, wherein the thin film metal comprises a nickel titanium alloy.

CLAIMS.

We claim:

1. An embolic protection device, comprising:
a first elongate member having a lumen;
5 a second elongate member extending through the lumen and being movable with respect to the first elongate member; and
a graft member having a proximal end portion connected to the first elongate member and a distal end portion connected to the second elongate member, and a plurality of openings extending through the graft member along a length thereof;
10 the graft member being expandable from an undeployed generally tubular state to a deployed generally frustoconical state upon relative movement between the first and second elongate members in a first direction, the openings generally decreasing in size from the proximal end toward the distal end when the graft member is in the deployed state to thereby capture and retain emboli and other particulate matter of different sizes.
- 15 2. An embolic protection device according to claim 1, wherein the openings are substantially uniform in size when the graft member is in the undeployed state.
3. An embolic protection device according to claim 1, and further comprising a plurality of arm members extending between the first elongate member and the proximal end of the graft member, such that relative movement of the first and second elongate members in the
20 first direction causes the arm members to move from a generally axial orientation to a generally radial orientation to thereby radially expand the proximal end of the graft member.
4. An embolic protection device according to claim 3, wherein the distal end of the graft member is substantially restrained against radial expansion such that the diameter of the graft member decreases from the proximal end toward the distal end when the graft member is
25 in the deployed state.
5. An embolic protection device according to claim 4, wherein the size of each opening is proportional to the diameter of the graft member at which each opening is located.

30

16. An embolic protection device according to claim 1, wherein the graft member is constructed of braided wire.

17. An embolic protection device according to claim 1, wherein the first elongate member is a catheter.

5 18. An embolic protection device according to claim 17, wherein the second elongate member is a guide wire.

19. An embolic protection device according to claim 18, wherein the guide wire has an atraumatic tip at a distal end thereof.

20. An embolic protection device according to claim 1, wherein the second elongate
10 member has a tubular distal portion, and further comprising a plurality of arm members integrally formed in the tubular portion in proximity with the proximal end of the graft member, the plurality of arm members being biased toward an expanded arm position and normally restrained in a retracted arm position by the first elongate member, such that relative movement of the first and second elongate members in the first direction causes the arm members to move
15 from the retracted arm position toward the expanded arm position to thereby radially expand the proximal end of the graft member.

21. An embolic protection device comprising:
a catheter body having a central longitudinal lumen;
a guidewire having an atraumatic tip positioned at a distal end thereof, the
20 guidewire being coaxially positioned within the central longitudinal lumen of the catheter body;
and

a graft member movable between an undeployed state and a deployed state, the graft member being of a generally tubular shape in the undeployed state and of a generally frustroconical shape in the deployed state, the graft member comprising a plurality of openings
25 extending along a longitudinal axis thereof, with a distal end of the graft member being connected to one of the guidewire and the atraumatic tip, the graft member being movable between the undeployed and deployed states upon relative movement between the catheter body and the guide wire, the graft member being constructed of a material such that each opening expands and reduces in size in proportion to an amount of radial expansion and
30 reduction, respectively, of a corresponding transverse cross sectional region of the graft member with which the opening is associated, to thereby capture emboli and other particulate

matter when the graft member is in the deployed state and minimize extrusion of the captured material through the openings in the graft member when the graft member is in the undeployed state.

22. An embolic protection device according to claim 21, wherein the openings are
5 substantially uniform in size when the graft member is in the undeployed state.

23. An embolic protection device according to claim 22, wherein the graft member is constructed from at least one of a superelastic material, a plastically deformable material, and an elastic material.

24. An embolic protection device according to claim 21, wherein the graft member
10 is constructed from at least one of a superelastic material, a plastically deformable material, and an elastic material.

25. An embolic protection device according to claim 21, wherein the distal end of the graft member is substantially restrained against radial expansion such that the graft member decreases in diameter from the proximal end toward the distal end when the graft member is in
15 the deployed state.

26. An embolic protection device according to claim 21, wherein the graft member is constructed of a metal material.

27. An embolic protection device according to claim 21, wherein the graft member is constructed of a thin film metal.





20 28. An embolic protection device according to claim 27, wherein the thin film metal comprises a nickel titanium alloy.

29. An embolic protection device according to claim 21, wherein the graft member is constructed of braided wire.



230. An embolic protection device according to claim 21, wherein the guidewire has
25 a tubular portion, and further comprising a plurality of arm members integrally formed in the tubular distal portion in proximity with the graft member, the tubular arm members being biased toward an expanded arm position and normally restrained in a retracted arm position by the catheter body, such that relative movement of the guidewire and catheter body direction causes the arm members to move from the retracted arm position toward the expanded arm
30 position to thereby radially expand the proximal end of the graft member.

31. An embolic protection device according to claim 30, wherein the arm members are constructed of braided wire.




1/5



2/5



3/5



4/5




FIG. 9A




FIG. 9B

5/5




FIG. 10A




FIG. 10B

**(19) World Intellectual Property Organization
International Bureau**



(43) International Publication Date
27 February 2003 (27.02.2003)

(10) International Publication Number
WO 03/015840 A3

PCT


- (51) **International Patent Classification⁷:** A61M 29/00
- (21) **International Application Number:** PCT/US02/24578
- (22) **International Filing Date:** 1 August 2002 (01.08.2002)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
60/313,294 17 August 2001 (17.08.2001) US
10/136,246 29 April 2002 (29.04.2002) US
- (71) **Applicant (for all designated States except US):** **ADVANCED BIO PROSTHETIC SURFACES, LTD.** [US/US]; 4778 Research Drive, San Antonio, TX 78240 (US).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** **BOYLE, Christopher, T.** [US/US]; 7667 Callaghan, #601, San Antonio, TX 78229 (US). **BAILEY, Steven, R.** [US/US]; 3 Village Knoll, San Antonio, TX 78232 (US).
- (81) **Designated States (national):** AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) **Designated States (regional):** ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report

Published:

— with international search report

[Continued on next page]

(54) Title: EMBOLIC PROTECTION DEVICE



(57) Abstract: An embolic protection device (10) includes a catheter body (14) having a central longitudinal lumen, a guidewire (12) positioned within the central longitudinal lumen, and a graft member (16) that is generally tubular in shape in an undeployed state and generally frustoconical in shape in a deployed state. A plurality of openings (30) are formed in the graft member (16) and a plurality of arm members (18) interconnect a proximal end of the graft member with the catheter body. The graft member may be fabricated of superelastic materials, plastically deformable materials or self-expanding materials and the plurality of openings are capable of diametric expansion and reduction proportionate to the degree of diametric expansion and reduction of a corresponding transverse cross-sectional region of the graft member when in the deployed state to capture emboli or particulate matter and minimize extrusion of the captured material through the openings in the graft member when the graft member is collapsed.

WO 03/015840 A3



(88) Date of publication of the international search report:
4 December 2003

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US02/24578

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) :A61M 29/00

US CL :606/200

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 606/200

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

NONE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X, P	US 6,277,139 A (LEVINSON et al) 21 August 2001, figures 1-10.	1-19, 21-29

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"G" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

21 NOVEMBER 2002

Date of mailing of the international search report

19 MAY 2003

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

KEVIN TRUONG

Telephone No. (703) 308-0858

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.